



CCRMP

Canadian Certified Reference Materials Project

CANMET Mining and Mineral Sciences Laboratories
555 Booth Street, Ottawa, Canada K1A 0G1

Tel.: (613) 995-4738, Fax: (613) 943-0573
E-mail: ccrmp@nrcan.gc.ca
www.ccrmp.ca

PCMRC

Projet canadien de matériaux de référence certifiés

Laboratoires des mines et sciences minérales de CANMET
555, rue Booth, Ottawa, Canada K1A 0G1

Tél.: (613) 995-4738, Téléc.: (613) 943-0573
Courriel: pcmrc@nrcan.gc.ca
www.pcmrc.ca

Certificate of Analysis

June 1995

SY-4

Diorite Gneiss Reference Material

Certified Values \pm 95% Confidence Interval

Al ₂ O ₃	20.69	\pm 0.08	%	MnO	0.108	\pm 0.001	%
CaO	8.05	\pm 0.04	%	Na ₂ O	7.10	\pm 0.05	%
CO ₂	3.5	\pm 0.1	%	P ₂ O ₅	0.131	\pm 0.004	%
Fe ₂ O ₃ total	6.21	\pm 0.03	%	SiO ₂	49.9	\pm 0.1	%
FeO	2.86	\pm 0.09	%	TiO ₂	0.287	\pm 0.003	%
K ₂ O	1.66	\pm 0.02	%	LOI	4.56	\pm 0.07	%
MgO	0.54	\pm 0.01	%				

Ba	340	\pm 5	μ g/g	Nd	57	\pm 1	μ g/g
Be	2.6	\pm 0.1	μ g/g	Ni	9	\pm 1	μ g/g
Ce	122	\pm 2	μ g/g	Pb	10	\pm 1	μ g/g
Co	2.8	\pm 0.2	μ g/g	Pr	15.0	\pm 0.3	μ g/g
Cr	12	\pm 1	μ g/g	Rb	55	\pm 1.5	μ g/g
Cs	1.5	\pm 0.1	μ g/g	Sc	1.1	\pm 0.1	μ g/g
Cu	7	\pm 1	μ g/g	Sm	12.7	\pm 0.4	μ g/g
Dy	18.2	\pm 0.6	μ g/g	Sr	1191	\pm 12	μ g/g
Er	14.2	\pm 0.5	μ g/g	Ta	0.9	\pm 0.1	μ g/g
Eu	2.00	\pm 0.04	μ g/g	Tb	2.6	\pm 0.1	μ g/g
Ga	35	\pm 1	μ g/g	Th	1.4	\pm 0.2	μ g/g
Gd	14.0	\pm 0.5	μ g/g	Tm	2.3	\pm 0.1	μ g/g
Hf	10.6	\pm 0.4	μ g/g	U	0.8	\pm 0.1	μ g/g
Ho	4.3	\pm 0.1	μ g/g	V	8	\pm 1.6	μ g/g
La	58	\pm 1	μ g/g	Y	119	\pm 2	μ g/g
Li	37	\pm 2	μ g/g	Yb	14.8	\pm 0.4	μ g/g
Lu	2.1	\pm 0.1	μ g/g	Zn	93	\pm 2	μ g/g
Nb	13	\pm 1	μ g/g	Zr	517	\pm 16	μ g/g



Natural Resources
Canada

Ressources naturelles
Canada

Canada

DESCRIPTION

SY-4 is a diorite gneiss obtained from an outcrop of the Rosenthal-Reid Lake Belt in Brudenell Township, Renfrew County, Ontario, Canada. It is intended as a replacement for the popular rock reference material, SY-2, which is now depleted.

Over 350 kg of rock was collected. This was dried, cleaned, broken, crushed and ground to $-74 \mu\text{m}$ (-200 mesh). The powdered material was blended and bottled in 100-g lots. The analyses for homogeneity assessment were performed by the Geological Survey of Canada (GSC). This involved a complete whole-rock analysis along with barium, strontium, rubidium and zirconium on 22 bottles chosen according to a stratified random sampling scheme. The analysis was done in duplicate using a fused-disk X-ray fluorescence technique.

Mineralogical investigation of SY-4 revealed major amounts of oligoclase and scapolite and minor amounts of biotite, calcite and analcime along with trace amounts of magnetite and apatite.

CERTIFICATION

Eighty-nine university, commercial, and government laboratories from all over the world participated in an interlaboratory certification program. Up to 80 elements were analyzed by methods of each laboratory's

choice. A statistical analysis of the data yielded recommended values for 49 constituents and provisional values for 8 more.

LEGAL NOTICE

The Canadian Certified Reference Materials Project has prepared this reference material and statistically evaluated the analytical data of the inter-laboratory certification program to the best of its ability. The purchaser, by receipt hereof, releases and indemnifies the Canadian Certified Reference Materials Project from and against all liability and costs arising out of the use of this material and information.

REFERENCE

The preparation and certification procedures used for SY-4 will be published. Copies of this report will be made available free of charge on application to:

Coordinator, CCRMP
CANMET (NRCan)
555 Booth Street
Ottawa, Ontario, Canada
K1A 0G1

Telephone: (613) 995-4738
Facsimile: (613) 943-0573

Provisional Values \pm 95% Confidence Interval

C	1.0 \pm 0.1	%	H ₂ O-	0.15 \pm 0.05	%
F	0.06 \pm 0.01	%	S ^{total}	0.015 \pm 0.004	%
H ₂ O+	1.0 \pm 0.3	%			
Ag	0.6 \pm 0.16	$\mu\text{g/g}$	Sn	7.1 \pm 0.6	$\mu\text{g/g}$
Br	217 \pm 14	$\mu\text{g/g}$			

Information Values (Range)

Cl	0.3 - 0.6	%	SO ₃	0.01 - 0.08	%
As	0.1 - 2	$\mu\text{g/g}$	Mo	0.2 - 3	$\mu\text{g/g}$
B	13 - 18	$\mu\text{g/g}$	Sb	0.01 - 0.3	$\mu\text{g/g}$
Bi	0.1 - 0.3	$\mu\text{g/g}$	Se	0.01 - 4	$\mu\text{g/g}$
Cd	0.1 - 2	$\mu\text{g/g}$	Tl	0.2 - 0.5	$\mu\text{g/g}$
Ge	1 - 4	$\mu\text{g/g}$	W	0.2 - 15	$\mu\text{g/g}$
Hg	10 - 14	ng/g*			
In	0.04 - 0.1	$\mu\text{g/g}$			

* nng = 10^{-9} g/g (i.e., ppb)

Pour obtenir la version française du présent certificat d'analyse, prière de s'adresser au Coordinateur du PCMR.